





# Ref. MMR01812-75

# RO element for residential use

## SPECIFICATIONS:

General Features	
Permeate flow rate:	75 GPD (280 L/day)
Nominal salt rejection:	98,0 %
Effective membrane area:	4 ft² (0,37 m²)

1. The stated product performance is based on data taken after 30 minutes of operation at the following test conditions:

- 250 mg/L NaCl solution at 60 psig (0,41 MPa) applied pressure
- 15% recovery
- 77 °F (25 °C)
- pH 7,5 8,0


2. Permeate flow rate for each element may vary +/ -15 %.

3. Dry elements are packaged in a polyethylene bag.

Membrane type:	Thin-Film Composite
Membrane material:	Polyamide (PA)
Element configuration:	Spiral-Wound, FRP Wrapping

Operating Limits	
Max. pressure Drop / Element	10 psi (0,07 MPa)
Max. Operating Pressure	150 psi (1,03 MPa)
Max. Operating Temperature	45 °C (113 °F)
Operating pH Range	3,0-10,0
pH Range of Feed Water During Chemical Cleaning	2,0-12,0
Max. SDI (15 min)	5,0
Max. Chlorine Concentration	< 0,1 mg/L

### DIMENSIONS:



#### GENERAL HANDLING PROCEDURES

• Elements contained in the boxes must be kept dry at room temperature (7-32°C; 40-95°F) and should not be stored in direct sunlight. If the polyethylene bag is damaged, a new preservative solution (sodium bisulfite) must be added and air-tight sealed to prevent drying and biological growth.

· Permeate from the first hour of operation should be discarded to flush out the preservative solution.

• Elements should be immersed in a preservative solution during storage, shipping and system shutdowns to prevent biological growth and freezing. The standard storage solution contains 1% by weight sodium bisulfite or sodium metabisulfite (food grade). For short term storage (i.e. one week or less) 1% by weight sodium metabisulfite solution is adequate for preventing biological growth.

- Keep elements moist at all times after initial wetting.
- Avoid excessive pressure and flow spikes.
- Only use chemicals compatible with the membrane elements and components. Use of such chemicals may void the element limited warranty.

• Permeate pressure must always be equal or less than the feed/concentrate pressure. Damage caused by permeate back pressure voids the element limited warranty.

